


Technical Data Sheet

StoCrete TH 250

Bonding agent, sulphate-resistant, polymer-modified, cementitious



Characteristics

- Area of application**
- to ensure a permanent bond between the concrete substrate and the subsequent concrete repair system
 - for sulphate-contaminated substrates, e.g. in wastewater treatment plants
 - as bonding agent underneath concrete repair mortar for extremely aggressive sulphate-contaminated water in accordance with DIN 4030

Properties

- polymer modified, cementitious bonding agent (PCC), very good adhesive strength on a concrete substrate
- high sulphate resistance

Information/notes

- product is in accordance with EN 1504-3

Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Bulk density of fresh mortar	EN 1015-6	1.9 kg/dm ³	
Bond strength (28 days)	EN 1542	> 2.0 MPa	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Substrate

Requirements

Requirements on the substrate:

The concrete substrate must be load-bearing and free from native and foreign substances that have a separating action, as well as from corrosion-promoting components (e.g. chlorides). Remove less strong layers and laitance.

Damp in accordance with the definition in the DAfStb (German) Repair Guideline 2001-10.

Cleanliness grade of the exposed reinforcing steel after substrate preparation: Sa 2½ in accordance with EN ISO 8501-1.

Average bond strength 1.5 N/mm²

Bond strength of the single smallest value 1.0 N/mm²

Technical Data Sheet

StoCrete TH 250

Preparations

Prepare the substrate using a suitable mechanical process, such as abrasive blasting or high-pressure water blasting (> 800 bar).
Open pores and blow-holes sufficiently.

Bevel the edges of the areas of spalling under approx. 45°.

Note:

Rework any treated surfaces using a suitable process (abrasive blasting) if the substrate preparation process has led to joint faults in the area of the remaining old concrete close to the surface. These can result from chiselling, knocking, milling, or flame cleaning.

Application

Application temperature

Lowest application temperature: +5 °C
Highest application temperature: +30 °C

Time for application

At +5 °C: approx. 90 minutes
At +23 °C: approx. 60 minutes
At +30 °C: approx. 45 minutes

Mixing ratio

25 kg of material in accordance with the description / 5.75 - 6.25 l water = 1.0 : 0.23 - 0.25 parts by weight

Material preparation

Compulsory mixer: decant water and add pre-blended dry mortar. Stir for approx. 2 minutes. Allow to mature for approx. 3 minutes. Remix for approx. 30 seconds.

If using hand-held paddle mixers, they should be counter-rotating and interlocking. Ensure that the mixing paddles of the mixer are at least 1/3 of the diameter and and at least 2/3 of the height of the mixing container.

If using single mixing paddles, these must have two stirring rings that act using the principle of countercurrent flow. The speed should be up to approx. 500 rpm.

Consumption

Type of application	Approx. consumption	
as bonding agent	1.6	kg/m ²

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

Coating build-up

- 1) Substrate preparation
- 2) Protection against corrosion with StoCrete TK (for exposed reinforcement)
- 3) Mineral bonding agent with StoCrete TH 250
- 4) Concrete repair with StoCrete TG 252 or StoCrete TG 254

Technical Data Sheet

StoCrete TH 250

Application

- 1) Substrate preparation
- 2) Protection against corrosion
- 3) Mineral bonding agent, sulphate-resistant
Sufficiently pre-wet the concrete substrate before applying StoCrete TH 250 (about 24 hours before the first application cycle).
At the time of application, however, the concrete substrate must be dry to the point that it just appears slightly damp.

Use a brush to work the bonding agent into the prepared substrate.
Remove any cured bonding agent by blasting abrasive and renew it.
Consumption approx. 1.6 kg/m² as dry material
- 4) Concrete repair
Then apply the mixed mortar StoCrete TG 252 or StoCrete TG 254 to the fresh bonding agent in accordance with the Technical Data Sheets. To ensure a good adhesive bond, always work wet on wet.

Cleaning the tools Clean tools with water immediately after use.

Notes, recommendations, special information, miscellaneous The Declaration(s) of Conformity can be obtained from the StoCretec Technisches InfoCenter
General application instructions can be found at www.stocretec.de (Products) and in the latest issue of the "Technical Data Sheets" manual, in the appendix.

Delivery

Packaging sack

Article number	Name	Container
00717-001	StoCrete TH 250	25 kg bag

Storage

Storage conditions Store in dry conditions.

Storage life In the original container until ... (see packaging).

Identification

Product group Bonding agent

Safety This product is subject to compulsory labelling in accordance with the current EU directive.
You will receive an EU Safety Data Sheet with your first order.

Technical Data Sheet

StoCrete TH 250

Please observe the information regarding the handling of the product, its storage, and disposal.

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH
Gutenbergstr. 6
D-65830 Kriftel

Tel.: +49 6192 401-104
Fax: +49 6192 401-105
stocretec@sto.com
www.stocretec.de